

# CARBON BRUSHES

## electrographitic materials



GRADE	RESISTIVITY	FLEXURAL	HARDNESS	DENSITY	CONTACT	FRICTION	CURRENT	MAX
		STRENGTH			DROP	COEF.	DENSITY	SURFACE
	u OHM / m	Mpa	scleroscope	g/cm ^3	VOLTS		A/cm sqr	SPEED
AY	10	20.7	45	1.6	1.8	0.29	6-15	20
G70	11	29.4	45			0.29	12	50
258	19	18.6	39	1.6	1.8	0.19	10-15	31
N39	20	31	47	1.77	2.4	0.19	15.5	51
DE7000	48	38	83	1.71	2.5	0.19	15	51
N2000	48	32	71	1.56	2.5	0.19	15	41
234	51	27.6	62	1.5	2.4	0.19	10	31
DE3	51	31	70	1.62	2.4	0.19	15	41
DE8	51	34.5	85	1.68	2.4	0.19	15	41
N5000	51	34.5	85	1.6	2.4	0.19	10	41
AX5	53	17.2	54	1.56	2.4	0.19	15	41
DE2	53	25.5	72	1.64	2.4	0.19	15	41
DE9000	53	33.1	85	1.68	2.5	0.19	15.5	51
SA35	53	16.5	61	1.54	2.5	0.19	15	41
TA35R	53	16.5	61	1.54	2.5	0.19	15	41
TA35	55	15.5	57	1.55	2.4	0.19	15	41
N6000	60	13.8	66	1.55	2.5	0.19	15	41
TA45R	60.1	15.1	55	1.62	2.5	0.19	15.5	51
DE5	61	27.6	88	1.65	2.4	0.19	15	51
DE7	61	30.3	92	1.67	2.4	0.19	15	51
DE25	61	22.5	85	1.6	2.5	0.19	15.5	51
N19	61	19.3	76	1.61	2.5	0.19	10	41
SA40	61	10.3	53	1.5	2.5	0.19	15	51
SA4548	64	10.3	50	1.5	2.5	0.29	15	41
SA45	66	10	50	1.49	2.5	0.19	15	41
TA45	66	11.7	54	1.53	2.5	0.29	10	51
TA50R	66	12	57	1.62	2.5	0.19	15.5	51
N18	71	15.5	56	1.61	2.5	0.19	15.5	51
N48	71	13.8	59	1.58	2.5	0.19	15	51
SA50	71	6.9	50	1.49	2.5	0.29	15	51
TA50	71	8.8	55	1.53	2.4	0.19	15.5	51
SA4542	73	10.5	57	1.51	2.5	0.29	15	41
TA4542	73	9.9	59	1.57	2.4	0.29	15	41

The information provided above are typical values only. We reserve the right to modify material specifications at our discretion



### Head Office-Sydney

21 Amour St  
Revesby NSW 2212  
T: 02 9772 5600  
F: 02 9774 5677  
E: sales@morgancarbon.com.au

### Melbourne

5/23-25 Bunney Rd  
South Oakleigh VIC 3167  
T: 03 9551 2377  
F: 03 9551 2177  
E: mel@morgancarbon.com.au

### Perth

4/195 Bannister Rd  
Canning Vale WA 6155  
T: 08 9456 3711  
F: 08 9456 3716  
E: per@morgancarbon.com.au

### Brisbane

34 Aerodrome Rd  
Caboolture QLD 4510  
T: 07 5433 7100  
F: 07 5432 4899  
E: bri@morgancarbon.com.au

### Auckland

5c Clemway Place  
PO Box 21195  
Henderson Auckland 1231 New Zealand  
T: 09 836 9220 / 0800 CARBON (0800 227 266)  
F: 09 836 9129 / 0800 4 BRUSH (0800 427 874)  
E: sales@morgancarbon.co.nz